

MASCHINENGLATTES KRAFT PAPIER

IPACK STRONG PRO

TECHNISCHE WERTE

Eigenschaft	Standard	Einheit	Typische Werte				
Grammatur	ISO 536	g/m ²	60	70	75	80	90
Feuchtigkeitsgehalt	ISO 287	%	6,0				
Zugfestigkeit	ISO 1924-3	kN/m	6,5	6,9	7,1	7,2	7,4
			3,0	3,2	3,3	3,4	3,5
Opazität	ISO 2471	%	73	77	79	81	84
Luftdurchlässigkeit	ISO 5636-5	s	≥30	≥30	≥30	≥25	≥20
Berstfestigkeit	ISO 2758	kPa	260	320			300
Wasseraufnahme COBB'60	ISO 535	g/m ²	25				
Weißgrad ISO C/2°	ISO 2470-1	%	88				
Bendtsen Rauigkeit	ISO 8791-2	ml/min	230				

- ✓ sehr gute Parameter im Endprodukt wie **hohe Festigkeit** und **Glätte** sowie **hervorragende Formation**
- ✓ **hervorragende Bedruckbarkeit** und **perfekte Laufeigenschaften** für unterschiedliche Anwendungen in komplexen Verpackungsverarbeitungsprozessen
- ✓ perfekt für verschiedene **Beschichtungs-** und **Lackanwendungen**

VERFÜGBARE ZERTIFIZIERUNG:



The mark of
responsible forestry



This product is from
sustainably managed
forests and controlled
sources



ISO 9001
Quality
Management
Systems
CERTIFIED

ISO 14001
Environmental
Management
CERTIFIED

ISO 45001
Occupational
Health and Safety
Management
CERTIFIED

ISO 50001
Energy
Management
CERTIFIED



FOOD SAFETY SYSTEM
DNV
ISO 22000

- ✓ 100% ECF-Fasern

IN ÜBEREINSTIMMUNG MIT:

BfR XXXVI / FDA §§ 176.170 / FDA §§ 176.180 / Verordnung (EC) no 1907/2006 (REACH) /
Verordnung (EC) no 1935/2004 / Richtlinie 94/62/EC / EN 71-3 / D.M. 21/3/73